Vol. 46, 1976 No. 2

# THEREVIEW OF PHYSICAL CHEMISTRY OF JAPAN

Founded in 1926

# CONTENTS

Toshihiro Nakayama, Muneo Sasaki and Jiro Osugi: Pressure Effect on
the EDA-Complexes Formed between Mesitylene, Hexamethylbenzene
and Tetracyanoethylene in Carbon Tetrachloride5
Hisayuki Inoue, Kimihiko Hara and Jiro Osugi: The Reaction of Nitrile
with $lpha$ -Hydrogens under High Pressure I, Dimerization and Trimerization
of Malononitrile ······6
Hidemoto Nojima, Minoru Saito and Masaru Inagaki: Equilibrium
Distribution Coefficient of Stilbene-Azobenzene System7
Akira Otani: Explosion Reaction of Olefins, III Explosion Reaction of trans-
Butene-2-Oxygen Mixture ·····8
Shinji Takahashi and Hiroji Iwasaki: Evaluation and Correlation of the
Self-Diffusion Coefficients of Gaseous Methane8
S. D. Hamann: Comments on "Ion-Ion and Ion-Water Interactions at High Pressure"
Pressure"
Boris S. El'yanov: Some Notes in Connection with "Ion-Ion and Ion-Water
Interactions at High Pressure"9
Masaru Nakahara and Jiro Osugi: On Ionic Activity Coefficients at High
Pressure

# THE PHYSICO-CHEMICAL SOCIETY OF JAPAN

# THE REVIEW OF PHYSICAL CHEMISTRY OF JAPAN

# (Butsuri-Kagaku no Shinpo)

Found in 1926

President: Wasaburo Jono

Members of Council:

Michio Okamoto (Chief)

Jiro Osugi

Ryozo Goto

Renpei Goto

Eiji Suito

Hiroyuki Hatano

## Board of Editors:

J. Osugi (Chief) Kyoto University

R. Goto (Associate) Kyoto Sangyo University

E. Suito ( " ) Osaka Institute of Technology

S. Shida

Yokohama University

H. Teranishi

Kyoto Technical University

K. Suzuki

Ritsumeikan University

K. Kuwata

University of Osaka

S. Seki

University of Usaka

R. Fujishiro

University of Osaka

Osaka City University

T. Hayakawa

\_\_\_\_\_\_\_\_\_\_

Prefectural University of Osaka

Y. Kubokawa

Prefectural University of Osaka

S. Tsuchihashi

Kobe University

T. Makita

Kobe University

S. Hasegawa

Okayama University

K. Shimizu

Doshisha University

H. Togawa

Doshisha University

## Secretary:

M. Sasaki

K. Hara

M. Nakahara

S. Fukase

# December 25, 1976

Communications to the Editor should be addressed to Board of Editors, The Physico-Chemical Society of Japan, Faculty of Science, Kyoto University, Kyoto, Japan.

Business Correspondences should be addressed to: Secretary, The Physico-Chemical Society of Japan, Faculty of Science, Kyoto University, Kyoto, Japan.

Purchase Order should be addressed to: Maruzen Co., Ltd., Nihonbashi, Chuo-ku, Tokyo, Japan.

# Published by

# THE PHYSICO-CHEMICAL SOCIETY OF JAPAN

(Nippon Butsuri-Kagaku Kenkyu Kai)
Faculty of Science, Kyoto University, Kyoto, Japan

Printed by KAWAKITA PRINTING CO., LTD., Kyoto, Japan

# Tell us about how you're using fluorine compounds.

Fluorine compounds have many unique qualities. But their usages today are only the beginning; the best is yet to come.

DAIKIN is a total maker of fluorine compounds.

Our series of them has been developed from Fluorspar as its basic material. And we've learned a lot along the way.

So the next time you discuss fluorine compounds,

think of DAIKIN—the company with all the answers. Answers we're anxious to share.

# DAIKIN Fluorochemicals

## **DAIKIN KOGYO CO LTD**

Head Office: Shin-Hankyu Bldg., 8 Umeda, Kita-ku, Osaka, Japan. Phone: Osaka (06) 346-1201 Telex: 523-3844

# The Review of Physical Chemistry of Japan

Vol. 46, 1976

# CONTENTS

# No. 1

Noriyuki Sotani: ESR Studies of the Hexagonal Hydrate of Molybdenum	
Oxide and Its Changes on Treatments in Vacuo and in Hydrogen	1
Noriyuki Sotani: The Reaction between Thiophene and Hydrogen on the	
Hexagonal Hydrate of Molybdenum Oxide	9
Etsuko Inada: The Pressure and Temperature Effects on the Walden Products	
of Na+, K+, Cs+ and I- in Water	19
Kiyoshi Shimizu, Noriaki Tsuchihashi and Yoshio Furumi: Effect of	
Pressure on Dissociation of Nickel Sulfate Ion Pair	30
Koichi Watanabe, Masahiko Uematsu and Shogo Saegusa: Thermodynamic	
Properties of Gaseous Propane and Propene	39
Erratum: T. Makita, Y. Tanaka and A. Nagashima, Rev. Phys. Chem. Japan,	
44, 98 (1974)	54
Erratum: M. Nakahara and J. Osugi, Rev. Phys. Chem. Iapan, 45, 69 (1975)	56
No. 2	
Toshihiro Nakayama, Muneo Sasaki and Jiro Osugi: Pressure Effect on	
the EDA-Complexes Formed between Mesitylene, Hexamethylbenzene	
and Tetracyanoethylene in Carbon Terrachloride	57
Hisayuki Inoue, Kimihiko Hara and Jiro Osugi: The Reaction of Nitrile	
with $\alpha$ -Hydrogens under High Pressure I, Dimerization and Trimerization	
of Malononitrile	64
Hidemoto Nojima, Minoru Saito and Masaru Inagakki: Equilibrium	
Distribution Coefficient of Stilbene-Azobenzene System	76
Akira Otani: Explosion Reaction of Olefins, III Explosion Reaction of trans-	
Butene-2-Oxygen Mixture	82
Shinji Takahashi and Hiroji Iwasaki: Evaluation and Correlation of the	
Self-Diffusion Coefficients of Gaseous Methane	88
S. D. Hamann: Comments on "Ion-Ion and Ion-Water Interactions at High	
Pressure"	95
Boris S. El'yanov: Some Notes in Connection with "Ion-Ion and Ion-Water	
Interactions at High Pressure"	96
Masaru Nakahara and Jiro Osugi: On Ionic Activity Coefficients at High	
Pressure	100


Published by

# THE PHYSICO-CHEMICAL SOCIETY OF JAPAN

Faculty of Science, Kyoto University, Kyoto, Japan

# We serve.... Many peoples, Many lands, Many ways.

SYNTHETIC RESINS & PLASTICS INDUSTRIAL CHEMICALS FERTILIZERS DYESTUFFS AGRICULTURAL CHEMICALS MEDICINES CONSTRUCTION AND BUILDING MATERIALS



MITSUI TOATSU CHEMICALS, INC. 2-5, Kasumigaseki 3-chome, Chiyoda-ku, Tokyo, Japan Cable: "MITSUITOATSU TOKYO"

Telex: Call No.0222-3622 Answer Back Code (MTCHEM J)

# HORIBA, Ltd. offers special application of

# RADIATION

# Ge(Li)γRay Detector



A coaxial type semiconductor detector made from a lithium-drifted Germanium single crystal. Ideally suitable for precision analysis of  $\gamma$  ray spectrum for its superb energy resolution.

- Energy Resolution: 1.9~1.6 keV
- Ambient radioactivity monitoring.
- Radiochemistry analysis.
- γ ray measurements in nuclear medicine.

## Silicone Detector Unit for Radiation

Semi-conductor detector units having surface barrier type silicone (semi-conductor) as elements ideally suitable for the measurements of alpha particles, fission fragments or heavy ions. Their measurable energy ranges are, approx. 9.5 MeV with an effective thickness of 60µ for alpha particles and approx. 15 MeV with 120µ, having resolutions ranging from 30 keV to 90 keV.

Recommendation for application is also a part of our service.


A spectrum of natural radioactivity in indoor atmosphere measured by Ge (Li) gamma ray detector. GL C92H (equivalent


to 50cc) Duration of Measurement: 100,000 sec. Counts Bias Voltage: +2,400v (Numerals at the peaks indicate gamma ray energy(keV).) ZIZR 206T /

# Si(Li)XRay Detector



This is a semi-conductor radiation detector made from lithium-drifted silicone single crystal, and because of its highest grade resolution expectable from an energy dispersion X ray detector, a simultaneous measurements of multiple elements is possible. It has a wide range of applications such as element analysis of pollutants like suspending 300 1000 1100 1200 1300 dust in atmosphere, X ray Channel Numbers (Energies) micro-analysis or X ray diffraction.





# Nal(TI) Scintillators for Radiation Measurement


These are the radiation detectors resorting to the phenomenon of a transparent single crystal to scintillate by the incident radiation. They are used for a general counting of gamma rays or soft X rays or for scintillation spectrometer. For meeting different applications, they are made to a variety of types such as standard type, well type, soft X ray type, union type, differential type, side-hole type or scinti-camera type.

# HORIBA, Ltd. ORIBA

Miyanohigashi, Kisshoin, Minami-ku, Kyoto, Japan

Tel: 075-313-8121 Cable: HORIBA KYOTO

Telex: 5422130



# **KS TYPE DIA APPARATUS**

The super-high pressure generator developed by Kobe Steel, Ltd. is called the KS type DIA apparatus. The apparatus is used for the research on the solid state physics, synthesizing new substances, producing man-made diamonds and various other experiments in the field of high pressure on solid.

Model No.	DIA-6	DIA-10	DIA-15	DIA-20
Working pressure (kilobars)	100	80	80	60
Working temperature (°C) (under the pressure above)	1,500	1,500	1,500	1,500
Dimensions of sample holder (mm)	6×6×6	10×10×10	15×15×15	20×20×20
Capacity of high pressure press (metric ton)	250	600	1,200	2,500
Input (not including power for heating)	750W 200V 50 or 60Hz	1,500W 200V 50 or 60Hz	1,500W 200V 50 or 60Hz	1,500W 200V 50 or 60Hz
Operation period (minute/cycle)	15	20	25	30

# **KOBE STEEL**

# MACHINERY & ENGINEERING DIVISION

- KOBE OFFICE 3-18, 1-chome, Wakinohama-cho, Fukiai-ku. Japan Phone: Kobe (078) 251-1551
- TOKYO OFFICE Tekko Bldg., 8-2, 1-chome, Marunouchi, Chiyoda-ku, Tokyo, Japan Phone:Tokyo (03) 218-7111